

### MA9 Tie-Coat

**ThistleBond 'MA9 Tie-Coat'** is a high performance anti-corrosive solvent based epoxy coating designed for use as a versatile universal primer for metallic and GRP substrates.

**ThistleBond 'MA9 Tie-Coat'** uses a well established blend of high molecular weight epoxy resin and a range of fine inorganic pigments and fillers combined with a specially formulated polyamine adduct which react together to product an effective anti-corrosive system with excellent adhesion to a wide range of surfaces whilst providing an extended overcoating window for most top coat finish Systems.

**Before proceeding, please read the following information carefully to ensure that the correct application procedure is fully understood.**

#### SURFACE PREPARATION

All oil and grease must be removed by thoroughly degreasing with **ThistleBond 'SFE Thinners'**.

**Steel Surfaces:** All rust and millscale must be completely removed. The preferred method for removal of rust and millscale is abrasive blast cleaning to a minimum of SA2½ to British Standard 7079 Part A1:1989 or equivalent near white finish. Where blast cleaning is not possible surfaces should be thoroughly cleaned by grinding or needle gunning.

**Galvanised Steel:** All oil and grease must be removed by thoroughly decreasing with **ThistleBond 'SFE Thinners'**. Any zinc corrosion salts must be removed by abrasion or thorough wire brushing.

**Aluminium Surfaces:** All oil and grease must be removed by thoroughly degreasing and the metal surface should then be abraded or lightly abrasive blasted.

**Polyester/GRP Surfaces:** Abrade with 240 grade abrasive paper to provide a uniformly etched surface.

#### MIXING

**ThistleBond 'MA9 Tie-Coat'** is a two component material which must be mixed together prior to use.

The resin component should be thoroughly stirred to incorporate any slight separation then the total contents of the hardener container should be added and stirring continued until a homogeneous mix is achieved.

The mixed material must be used within 8 hours of mixing at temperatures of 20°C (68°F).

#### APPLICATION

Application should not be carried out when the temperature is below 7°C (45°F) nor when the relative humidity exceeds 90% or the surface to be coated is less than 3°C above the dew point.

**ThistleBond 'MA9 Tie-Coat'** can be applied by conventional, air assisted airless spray or airless spray. **ThistleBond 'MA9 Tie-Coat'** can be applied to small areas brush or roller.

**ThistleBond 'MA9 Tie-Coat'** is supplied ready for use for application by spray.

**Airless Spray Application:** Equipment with a 32:1 pump ratio should be used with an input pressure of 60 psi, 13-15 thou spray tips should be used.

**Conventional Spray:** Most types of equipment are suitable.

A typical set up using conventional spray equipment is:  
Pressure Pot  
Needle Setup 1.1-1.8mm

**ThistleBond 'MA9 Tie-Coat'** will require thinning for conventional spray application and may require thinning for airless spray application. Up to 30% **ThistleBond 'SFE Thinners'** may be added by volume.

All equipment must be cleaned IMMEDIATELY after use with **ThistleBond 'SFE Thinners'**.

#### Theoretical Coverage Rate

8.8 m<sup>2</sup> / litre at 50 microns dft (95 ft<sup>2</sup> / litre at 2 mils dft)

#### Recommended Film Thickness

Wet 125 microns (5 mils)

Dry 50 microns (2 mils)

## PHYSICAL CONSTANTS

**Mixing Ratio** 9 parts resin to 1 part hardener by volume.

**Appearance** Resin Thixotropic Liquid  
Hardener Clear Liquid

#### Drying & Cure times at 20°C

Usable Life	8 hours
Touch Dry	2 hours
Hard Dry	4 hours
Minimum Overcoating	4 hours
Maximum Overcoating	3 months
Full Cure	7 days

**Volume Solids** 44%

**V.O.C.** 504 gm/litre

**Shelf Life** Use within 2 years of purchase. Store in original sealed containers at temperatures between 5°C (40°F) and 30°C (86°F)

**Food Contact** Meets FDA requirements CFR 21.175.300 for food contact.

## PHYSICAL PROPERTIES

**Abrasion Resistance** 70mgm weight loss per 1000 cycles-1kg load-CS17 wheel  
ASTMD4060

**Impact Resistance** Direct-5mm (0.2 inch)  
BS 3900 E3 Reverse-2.5mm (0.1 inch)

**Dry Heat Resistance** 100°C (212°F)  
ASTMD2485

**Direct Pull Adhesion** 38kg/cm<sup>2</sup> (550psi)  
ASTMD4541 (abrasive blasted steel)

**Salt Fog Resistance** Excellent, unaffected after 5,000 hours exposure  
ASTMB117

**Tensile Shear Adhesion** 140kg/cm<sup>2</sup> (2000psi)  
ASTMD1002

**Humidity Resistance** Unaffected 5,000 hours exposure  
BS 3900 Part F2

**Scratch Resistance** No Failure 2.5kg (5.5 lbs) BS 3900 Part E2 load

## HEALTH AND SAFETY

As long as normal good practice is observed **ThistleBond 'MA9 Tie-Coat'** can be safely used.

Protective Gloves should be worn to prevent skin contact.

Vapour masks should be worn for spray application.

A fully detailed **Material Safety Data Sheet** is either included with the material or is available on request.

## PACKAGING

Supplied in 5 litre packs.

The information provided in this Product Data Sheet is intended as a general guide only and should not be used for specification purposes. The information is given in good faith but we assume no responsibility for the use made of the product or this information because this is outside the control of the company. Users should determine the suitability of the product for their own particular purposes by their own tests. Detailed specifications are available on request from the company.



[www.thistlebond.com](http://www.thistlebond.com)

**ThistleBond Division of E. Wood Ltd.**  
Standard Way, Northallerton,  
N. Yorks. U.K. DL6 2XA  
Tel: +44(0)1609 780170  
Fax: +44(0)1609 780438 & 777905  
E Mail: [info@thistlebond.com](mailto:info@thistlebond.com)

FOR FURTHER INFORMATION PLEASE CONTACT