

## Extended Life Super Metal Rebuilding System

**ThistleBond 'Extended Life Super Metal Rebuilding System'** is a high performance multi purpose synthetic metal repair compound which has been specifically developed for repairs requiring good mechanical strength combined with easy machining properties and where additional working time is essential during the application period.

**ThistleBond 'Extended Life Super Metal Rebuilding System'** contains a complex range of epoxy resins combined with a polyamino-amine curing system reinforced with a phosphor steel alloy to enhance the corrosion and chemical resistance of the over-all system.

**Before proceeding, please read the following information carefully to ensure that the correct application procedure is fully understood.**

### SURFACE PREPARATION

Heavy contamination due to oil or grease must be removed using **ThistleBond 'Cleaner'**.

All loose material, rust and surface contaminants, including existing coatings, must be removed and the surface roughened by using an angle grinder, needle gun or abrasive blasting. Where grinding or needle gunning is used, the surface should be cross-scored to improve adhesion. Care must be taken when angle grinding, to avoid polishing rather than roughening the surface.

Surfaces should be carefully degreased using **ThistleBond 'Cleaner'**. Cloths should be frequently changed to avoid spreading contamination. On deeply pitted surfaces or porous castings, **ThistleBond 'Cleaner'** should be worked into the surface by brush and washed off using excess cleaner.

Parts (for example, threads or bearing surfaces) which must remain in position during application but must not adhere to **ThistleBond 'Extended Life Super Metal Rebuilding System'** must be coated with **ThistleBond 'Release Agent'**.

### MIXING

**ThistleBond 'Extended Life Super Metal Rebuilding System'** is a two component material comprising resin and hardener components which must be mixed together prior to use.

Measure one volume of resin component and one volume of hardener component onto a clean mixing board or other suitable surface. The two components should then be thoroughly mixed until completely streak free.

The material should be used within 60 minutes of mixing at 20°C (68°F). This time will be reduced at higher temperatures and extended at lower temperatures.

### APPLICATION

The mixed **ThistleBond 'Extended Life Super Metal Rebuilding System'** should be pressed firmly onto the prepared area, working the material into any cracks and surface defects, taking care not to trap air in deeply pitted areas.

When required, a reinforcement tape can be used to improve the mechanical properties, or to bridge large gaps. The reinforcing Tape should be impregnated with the **ThistleBond 'Extended Life Super Metal Rebuilding System'** then stippled into the first layer of product applied to the repair. Further material should then be applied over the tape.

Once the **ThistleBond 'Extended Life Super Metal Rebuilding System'** has reached initial set the material can be separated from surfaces treated with **ThistleBond 'Release Agent'**.

Once the material has cured for a minimum of 12 hours at 20°C (68°F) sanding, grinding and machining etc can be carried out using standard engineering facilities.

All equipment must be cleaned IMMEDIATELY after use with **ThistleBond 'Cleaner'**.

**Volume Capacity**

392cc (23.94 cu ins) per kilo

**PHYSICAL CONSTANTS**

<b>Mixing Ratio</b>	<b>Resin</b>	<b>Hardener</b>	
	1	1	By volume
	1.15	1	By weight

<b>Appearance</b>	Resin	Dark Grey Paste
	Hardener	Light Grey Paste

**Drying & Cure**

<b>times at</b>	UsableLife	60 minutes
<b>20°C (68°F)</b>	Initial Set	4 hours
	Machining	12 hours
	Full Mechanical	5 days

**Volume Solids** 100%**V.O.C.** Nil

**Shelf Life** Use within 5 years of purchase. Store in original sealed containers at temperatures between 5°C (40°F) and 30°C (86°F).

**Operating Temperature**

	<b>Maximum</b>	<b>Continuous</b>
Dry Heat	250°C (480°F)	120°C (248°F)
Wet Heat	120°C (248°F)	70°C (158°F)

**Food Contact** Meets FDA requirements CFR 21.175.300 for food contact.

**PHYSICAL PROPERTIES**

<b>Flexural Strength</b>	560 kg/cm <sup>2</sup> (8000 psi)
ASTMD790	
<b>Compressive Strength</b>	700 kg/cm <sup>2</sup> (10000 psi)
ASTMD695	
<b>Tensile Shear Adhesion</b>	175 kg/cm <sup>2</sup> (2500 psi)
ASTMD1002	(Grit Blasted Steel)
<b>Heat Distortion</b>	60°C (140°F)
ASTMD648	
<b>Hardness (Shore D)</b>	85
ASTMD2246	
<b>Corrosion Resistance</b>	5,000 hours
ASTMB117	

**HEALTH AND SAFETY**

As long as normal good practice is observed **ThistleBond 'Extended Life Super Metal Rebuilding System'** can be safely used.

Protective gloves should be worn.

A fully detailed **Material Safety Data Sheet** is either included with the material or is available on request.

**PACKAGING**

Supplied in 3kg packs.

The information provided in this Product Data Sheet is intended as a general guide only and should not be used for specification purposes. The information is given in good faith but we assume no responsibility for the use made of the product or this information because this is outside the control of the company. Users should determine the suitability of the product for their own particular purposes by their own tests. Detailed specifications are available on request from the company.



[www.thistlebond.com](http://www.thistlebond.com)

**ThistleBond Division of E. Wood Ltd.**  
**Standard Way, Northallerton,**  
**N. Yorks. U.K. DL6 2XA**  
**Tel: +44(0)1609 780170**  
**Fax: +44(0)1609 780438 & 777905**  
**E Mail: info@ thistlebond.com**

FOR FURTHER INFORMATION PLEASE CONTACT