

## Abrasion Resistant Ceramic Carbide Fluid

**ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** is a high performance fluid grade engineering resurfacing compound designed for use in fluid flow environments.

**ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** uses a complex blend of epoxy resins and a polyamino-amide curing system reinforced with carbide and ceramic particles to produce a coating with a high level of abrasion and erosion resistance combined with optimum physical and mechanical strength.

**ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** offers outstanding protection against impingement, entrainment and erosion / corrosion conditions.

**Before proceeding, please read the following information carefully to ensure that the correct application procedure is fully understood.**

### SURFACE PREPARATION

All dust and loose material should be scraped away. Oil and grease should be removed with **ThistleBond 'Cleaner'**. Surfaces should then be abrasive blast cleaned to a minimum Sa2½ BS7079 Part A1 : 1989 or equivalent with a blast profile of 75 microns (3 mil) corresponding to 'Medium' in BS7079 Part C3/ISO 8503/1. All loose abrasive dust and debris must be blown clear or vacuum cleaned away.

Equipment which has become salt impregnated due to service conditions should, first be wet blasted then dry abrasive blasted and checked for presence of salts. This process should be repeated until the salts are removed.

Alternatively, surfaces should be warmed with a blow torch or heat gun to bring salts up to the surface. The surface should once again be blast cleaned. This process must be repeated until no further sweating of impregnated salts is evident.

On sections of repair which are not required to bond to the **ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** these surfaces should be treated with **ThistleBond 'Release Agent'**.

### MIXING

**ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** is a two component material comprising resin and hardener components which must be mixed together before use.

Mix the entire contents of the resin and hardener containers.

Alternatively measure three volumes of resin component and one volume of hardener into a clean container. The two components should be thoroughly mixed until completely streak free.

The mixed material should be used within 25 minutes of mixing at 20°C (68°F). This time will be reduced at higher temperatures and extended at lower temperatures.

### APPLICATION

Application should not be carried out at temperatures below 5°C nor when relative humidity exceeds 85% or when the surface to be coated is less than 3°C above the dew point.

The mixed material should be applied to the prepared area using a clean brush or squeegee, application should be carried out as soon as possible after surface preparation is complete, and certainly the same day, otherwise flash blasting will be necessary before application.

Where necessary a reinforcement tape should be stippled into the mixed product and further material applied over the tape. For large areas the tape should be overlapped.

In areas where a second layer of **ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** is required, this application must be carried out within the initial set time for the first layer, otherwise the surface must be lightly abraded or flash blasted.

Machining of **ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** will cause excessive tool wear so care should be taken to finish the repair to the required size or dimensions. Formers treated with **ThistleBond 'Release Agent'** can be used to minimise machining.

All equipment must be cleaned IMMEDIATELY after use with **ThistleBond 'Cleaner'**.

**Theoretical Coverage Rate**

1.75m<sup>2</sup>/kilo at 250 microns dft (19 ft<sup>2</sup> per kilo at 10 mils)

**Volume Capacity**

440 cc (27 cu ins) per kilo

**Typical Film Thickness**

Wet 250 microns (10 mils)

Dry 250 microns (10 mils)

Normally applied as a two coat system to achieve a nominal film thickness of 500 microns.

**PHYSICAL CONSTANTS**

Mixing Ratio	Resin	Hardener	
	3	1	By volume
	8	1	By weight

Appearance	Resin	Hardener	Coloured Paste
			Amber Liquid

**Drying & Cure times**

at 20°C/68°F	Usable Life	25 minutes
	Initial Set	3 hours
	Grinding Time	6 hours
	Full Mechanical	5 days

**Volume Solids** 100%

**V.O.C.** Nil

**Shelf Life** Use within 5 years of purchase. Store in original sealed containers at temperatures between 5°C (40°F) and 30°C (86°F).

**Food Contact** Meets USDA requirements for incidental food contact.  
Meets FDA requirements CFR21.175.300 for food contact.

FOR FURTHER INFORMATION PLEASE CONTACT



**Operating**

Temperature	Maximum	Continuous
Dry Heat	250°C (480°F)	120°C (248°F)
Wet Heat	120°C (248°F)	70°C (158°F)

**PHYSICAL PROPERTIES**

<b>Compressive Strength</b>	915 kg/per cm <sup>2</sup> (13000 psi)
ASTMD695	
<b>Tensile Strength</b>	195 kg/per cm <sup>2</sup> (2800 psi)
ASTMD1002	
(Grit blasted steel)	
<b>Flexural Strength</b>	635 kg/per cm <sup>2</sup> (9000 psi)
ASTMD790	
<b>Rockwell Hardness</b>	100
ASTMD785	
<b>Abrasion Resistance</b>	0.065 ml loss per 1000 cycles
ASTM D4060	(CS17 wheel 1 kg load)
<b>Heat Distortion</b>	60°C (175°F)
<b>Temperature</b>	
ASTMD648	
<b>Corrosion Resistance</b>	5000 hours
ASTMB117	

**HEALTH AND SAFETY**

As long as normal good practice is observed **ThistleBond 'Abrasion Resistant Ceramic Carbide Fluid'** can be safely used.

Protective gloves should be worn.

A fully detailed **Material Safety Data Sheet** is either included with the material or is available on request.

**PACKAGING**

Supplied in 1kg packs.

The information provided in this Product Data Sheet is intended as a general guide only and should not be used for specification purposes. The information is given in good faith but we assume no responsibility for the use made of the product or this information because this is outside the control of the company. Users should determine the suitability of the product for their own particular purposes by their own tests. Detailed specifications are available on request from the company.



[www.thistlebond.com](http://www.thistlebond.com)

**ThistleBond Division of E. Wood Ltd.**  
Standard Way, Northallerton,  
N. Yorks. U.K. DL6 2XA  
Tel: +44(0)1609 780170  
Fax: +44(0)1609 780438 & 777905